



Citation 2


INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61F 2/01, A61B 17/12		A1	(11) International Publication Number: WO 95/25480
			(43) International Publication Date: 28 September 1995 (28.09.95)
(21) International Application Number: PCT/US95/03380		(81) Designated States: AU, CA, JP, KP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 16 March 1995 (16.03.95)			
(30) Priority Data: 08/210,798 18 March 1994 (18.03.94) US		Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(71) Applicant: COOK INCORPORATED [US/US]; 925 South Curry Pike, Bloomington, IN 47402 (US).			
(72) Inventor: TEKULVE, Kurt, J.; 851 Woodbridge Drive, Bloomington, IN 47408 (US).			
(74) Agent: GODLEWSKI, Richard, J.; P.O. Box 2256, West Lafayette, IN 47906 (US).			

(54) Title: **HELICAL EMBOLIZATION COIL**

(57) Abstract

A conically helically shaped embolization coil (10) for occluding a blood vessel, aneurysm, and the like. The embolization coil includes a continuous platinum-tungsten alloy wire strand (11) wound into a longitudinally extending coil (12) having a plurality of tightly spaced turns (13). The longitudinally extending coil is wound into a conically helically shaped coil (15) with a plurality of radially expanding turns (16) that has spacing that increases proximally from the distal end (29) of the coil. Distal turn (17) of the radially expanding turns has a minor diameter (18) less than a minimum diameter (34) of a vessel (32) of which the embolization is to be positioned therein. Uncompressed proximal turn (19) of the radially expanding turns has a major diameter (20) greater than a maximum diameter (33) of the vessel in which the coil is to be positioned. The conically helically shaped coil and particular diameter ensure that the coil is precisely positioned in a vessel lumen without longitudinal displacement of the delivery catheter. The coil is stress relieved and, in particular, heat treated by heating the coil to a stress relief temperature of the continuous wire strand and cooled to relieve residual stresses formed during the winding of the coil and to minimize the formation of new residual stresses formed during the cool down period of the heat treatment. Thrombogenic fibers (26) are positioned in the tightly spaced turns of the coil to attract thrombus and build up a mass that occludes the vessel lumen.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

HELICAL EMBOLIZATION COIL

DescriptionTechnical Field

This invention relates generally to embolization coils and, in particular, to an embolization coil that is conically helically shaped.

Background of the Invention

Intravascular interventional procedures for providing an artificial embolism are desirable in some patients for controlling internal bleeding, preventing blood supply to tumors, or relieving pressure in the vessel wall near an aneurysm. Several approaches are known for providing an artificial embolism, including the use of an inflatable, detachable balloon or the injection of a coagulative substance. Another approach utilizes an occlusive wire coil and delivery system for positioning the coil at a desirable site in a blood vessel.

One wire coil and delivery system includes a flexible, coiled wire that when released from the distal end of a delivery catheter assumes a randomly coiled, space-filling mass. The wire is released from the catheter by a pusher catheter with a closed distal end for engaging the proximal end of the coil. A problem with this system is that the wire coil is just pushed out the distal end of the delivery catheter toward the target embolism site and then assumes a folded, convoluted configuration. This folded, convoluted configuration is obtained with the use of an occlusion wire that possesses memory which returns the wire from a stretched to a relaxed convoluted condition. One problem with this convoluted configuration coil is that precise positioning of the coil at the occlusion site is difficult to obtain. This is mainly due to the coiled configuration of the wire in which the distal end of the convoluted wire engages the wall of the vessel and longitudinally displaces the delivery catheter. As a result, the delivery catheter and occlusion coil are proximally displaced from the desired occlusion site. Such longitudinal displacement

can readily prevent an aneurysm from being occluded. Furthermore, the displaced convoluted coil, which is to be positioned in, for example, an aneurysm, then proceeds downstream and causes an occlusion at an undesired site. This can cause
5 additional pressure to be applied to the already weakened wall of the aneurysm.

Another problem with this convoluted coil is ensuring that sufficient mass is positioned across the cross-sectional area of the vessel lumen to sufficiently restrict blood flow.

10

Summary of the Invention

The foregoing problems are solved and a technical advance is achieved in an illustrative embolization coil that is conically helically shaped with a plurality of radially expanding
15 turns. The distal turn of the radially expanding turns has a minor diameter less than the minimum diameter of a vessel in which the embolization coil is to be positioned. This advantageously allows for precise positioning of the coil at the embolization site. The distal end of the coil is introduced from
20 a delivery catheter into the central region of the vessel without longitudinally displacing the delivery catheter from the occlusion site. As the proximal radially increasing turns of the coil expand against the interior surface of the vessel wall, the embolization coil is fixedly positioned in the vessel with the
25 longitudinal axis of the coil being substantially aligned with that of the vessel lumen. The uncompressed proximal turn of the coil has a major diameter greater than the maximum diameter of the vessel to advantageously expand against the interior surface of the vessel wall. As a result, the conically helically shaped
30 coil is fixedly and precisely positioned in the vessel at the occlusion site. Furthermore, the radially expanding coil turns effectively covers the cross-sectional area of the vessel lumen, thus significantly reducing blood flow through the coil.

To further occlude the vessel, the embolization coil
35 includes a continuous wire strand that is wound into a longitudinally extending coil with a plurality of tightly spaced turns. Thrombogenic fibers are positioned in the tightly spaced

turns of the longitudinally extending coil to further attract thrombus thereto and quickly build up a mass that completely occludes the vessel.

To centrally position the embolization coil in substantial alignment with the longitudinal axis of the vessel lumen, the radially expanding turns of the conically helically shaped coil include spacing that increases proximally. This advantageously allows the embolization coil to be precisely and fixedly positioned at the occlusion site. The thrombogenic fibers positioned along the length of the coil and the proximally increasing turns also quickly build up a mass for occlusion of the vessel lumen.

For advantageously maintaining the conical helical shape of the coil, the continuous wire strand is stress relieved and, in particular, heat treated after the longitudinally extending coil is wound into a conical helical shape. The heat treatment advantageously relieves stresses that are formed when winding the longitudinally extending coil and the conically helically shaped coil. The heat treatment process includes heating the embolization coil at a stress relief temperature of the continuous wire strand for a first time period to relieve the residual stresses, and then gradually cooling down the coil from the stress relief temperature for a second time period greater than the first to minimize the introduction of new residual stresses during the cool down. Preferably, the continuous wire strand comprises a metallic alloy material, such as a platinum-tungsten alloy, that is substantially free of surface oxidation, which is considered a blood contaminant.

The conically helically shaped coil is formed by winding the longitudinally extending coil around a longitudinally tapered mandril with a plurality of minimally spaced turns. The mandril advantageously comprises a stainless steel material to minimize the formation of surface oxidation thereon during the heat treatment process. The metallic alloy material of the coil can also comprise at least one from a group consisting of platinum, stainless steel, iridium, palladium, tungsten, and gold. When wound around the tapered mandril, the coil is heated at the

stress relief temperature of the metallic alloy and then cooled. The conically helically shaped coil is removed from the mandril, at which time the spacing between the radially expanding turns increases proximally from the distal end thereof. The
5 embolization coil is then positioned in a cannula in which the coil is positioned therein in a delivery state for insertion into a guiding or delivery catheter.

Brief Description of the Drawing

10 FIG. 1 depicts an illustrative conically helically shaped embolization coil of the present invention longitudinally positioned in the vessel of a patient;

FIG. 2 depicts the distal turn of the embolization coil of FIG. 1 emerging from the distal end of a delivery catheter;

15 FIG. 3 depicts the embolization coil of FIG. 1 emerging from the distal end of a delivery catheter with only the proximal turn remaining in the delivery catheter;

FIG. 4 depicts a partially sectioned view of the embolization coil of FIG. 1 in an elongated condition prior to
20 being wound into a conically helically shaped coil;

FIG. 5 depicts the longitudinally extending coil of FIG. 4 wound around the tapered surface of a mandril to form a conically helically shaped coil;

25 FIG. 6 depicts the conically helically shaped coil of FIG. 5 after it has been removed from the mandril;

FIG. 7 depicts an end view of the conically helically shaped coil of FIG. 6; and

30 FIG. 8 depicts a partially sectioned view of a shipping cannula with the embolization coil of the present invention positioned therein.

Detailed Description

FIG. 1 depicts illustrative embolization coil 10 longitudinally positioned in vessel 32 of a human or animal body.
35 The embolization coil has been formed into conically helically shaped coil 15 having a longitudinal axis that is substantially aligned with the longitudinal axis of vessel 32. The conically

helically shaped coil has a plurality of radially expanding turns 16 with thrombogenic fibers 26 spaced at predetermined intervals along the length of the coil. The conically helically shaped coil extends over almost the entire cross-sectional area of vessel lumen 35 to substantially impede blood flow and attract thrombus. The thrombogenic fibers of the embolization coil more readily attract thrombus to further build up a mass that entirely occludes the vessel.

Due to the build up of plaque and other irregularities in the vessel wall, lumen 35 has a maximum diameter 33 and a minimum diameter 34 through any given length of the vessel. To ensure longitudinal alignment and fixed positioning of the embolization coil in the vessel lumen, distal turn 17 of coil 15 has a minor diameter 18 that is less than minimum diameter 34 of the vessel, and compressed proximal turn 19 of coil 15, when in an uncompressed condition, has a major diameter 20 that is greater than maximum diameter 33 of the vessel. This sizing of the conically helically shaped coil ensures that distal end 29 of the coil is introduced from a delivery catheter into the central region of the vessel. The successive turns of the coil radially increase in size as the embolization coil is released from the delivery catheter to engage and expand against the interior surface or intimal layer of the vessel wall. As a result, minor diameter distal turn 17 does not engage the vessel wall and longitudinally displace the delivery catheter positioned at the occlusion site. The proximal radially expanding turns of the coil centrally and longitudinally position the coil in the vessel lumen. Furthermore, the most proximal turns of the coil readily expand against the interior surface of the vessel wall and fixedly position the coil at the desired occlusion site. Precision positioning of the coil is thus readily achieved without concern for the embolization coil emerging from the delivery catheter and tumbling or drifting to an undesired occlusion site in the vessel.

FIG. 2 depicts embolization coil 10 of FIG. 1 positioned in a stretched or loaded condition in delivery catheter 36 and distal end 29 of turn 17 of the coil emerging from distal end 37

of the catheter. Distal end 29 of the coil is centrally positioned in vessel lumen 35 with distal turn 17 emerging from the delivery catheter. As a result, distal end 29 of the coil as well as distal turn 17 is introduced into the vessel lumen without longitudinally displacing delivery catheter 36 from the occlusion site in vessel 32.

FIG. 3 depicts embolization coil 10 of FIG. 1 emerging from distal end 37 of delivery catheter 36 in vessel lumen 35 with only proximal turn 19 remaining in the delivery catheter. As shown, the proximal radially expanding turns 16 of conically helically shaped coil 15 have emerged from the delivery catheter and expanded to compress against the interior surface of the vessel wall. As a result, the longitudinal axis of the conically helically shaped coil is centrally positioned in vessel lumen 35 and aligned with the longitudinal axis of the vessel. Furthermore, the introduction of the embolization coil at the occlusion site is accomplished without longitudinally displacing the delivery catheter or allowing the coil to flow or tumble in the blood stream to an undesired occlusion site. Additionally, the radially expanding turns accurately and securely position the embolization coil at the occlusion site in the vessel. When the embolization coil is fully released from the delivery catheter, the radially expanding turns of the coil extend almost over the entire cross-sectional area of the vessel lumen. This significantly reduces blood flow and further promotes thrombus formation on the coil and thrombogenic fibers 26 extending from the coil.

FIG. 4 depicts a partially sectioned view of embolization coil 10 of FIG. 1 in an elongated condition prior to being wound into a conically helically shaped coil. The embolization coil comprises continuous wire strand 11 that has been wound in a well-known manner into longitudinally extending coil 12 with a plurality of tightly spaced turns 13 and hollow passage 14 extending longitudinally therein. Continuous wire strand 11 comprises a metallic alloy material 22 that is substantially free of surface oxidation that is considered an undesired contaminant in the bloodstream of a patient. Preferably, the continuous wire

strand comprises a commercially available .003" diameter platinum wire with 8 percent tungsten. Other alternative alloys include well-known medical grade stainless steel along with alloys including at least one from a group consisting of platinum, iron, iridium, palladium, tungsten, and gold. These particular alloys exhibit extremely low levels of surface oxidation particularly when heat treated to relieve residual stresses formed during the winding of the embolization coil. Additionally, these metallic alloys are also considered thrombogenic to further promote thrombus formation and occlusion of the vessel at the occlusion site. The continuous wire strand is preferably wound into a longitudinally extending coil approximately 6 cm long with a .014" outside diameter and tightly spaced turns with minimal, if any, spacing therebetween. Distal end of the longitudinally extending coil is soldered or welded to present a rounded or smooth surface, which will not catch on the interior surface of the guiding catheter.

FIG. 5 depicts longitudinally extending coil of FIG. 4 wound around longitudinally tapered surface 38 of mandril 23 to form conically helically shaped coil with minimally spaced turns 24. Ends 39 and 40 of the longitudinally extending coil are positioned through respective transverse mandril holes 41 and 42 and bent to fixedly position the coil around longitudinally tapered surface 38. The outside diameter of mandril 23 preferably ranges from .250" to .325" with longitudinally tapered surface 38 necking down to a minimum diameter of .030" to .035". As a result, longitudinally tapered surface forms an angle with the longitudinal axis of the mandril of approximately 41 to 46 degrees. Since the wire strand and mandril are heat treated, mandril 23 comprises material 25 such as stainless steel that is heat treated in an oxygen free oven or another metal such as titanium or a metallic alloy that exhibits extremely low levels of surface oxidation after being heat treated. As suggested, the stainless steel mandril is placed in an oxygen free oven such as a commercially available argon oven to minimize surface oxidation during the heat treatment process.

Longitudinally extending coil 12 wound around longitudinally tapered mandril 23 to form conically helically shaped coil 15 is stress relieved and, in particular, heat treated to relieve residual stresses that formed during winding of the embolization coil. In particular, these residual stresses are formed when continuous wire strand 11 is wound into longitudinally extending coil 12 and, more importantly, when longitudinally extending coil 12 is wound around tapered mandril 23 to form conically helically shaped coil 15. By way of example, the longitudinally extending coil 12 and tapered stainless steel mandril 23 are positioned in a commercially available argon oven to minimize the formation of surface oxidation particularly on the stainless steel mandril during the heat treatment process. The coil and mandril are heated in the oven to a stress relief temperature of the platinum-tungsten alloy of approximately 1,012 degrees Fahrenheit for a first time period of approximately 2 hours to relieve stresses formed during the winding of the coil. The heated coil and mandril are then cooled down from this stress relief temperature for a second time period of, for example, 8 hours, which is much greater than the first 2-hour time period. This gradual cool down period minimizes the formation of new residual stresses that can be formed when the coil is cooled down too quickly.

As was previously suggested, the material of the embolization coil as well as that of the mandril is selected to be substantially free of surface oxidation that can be readily formed during the heating and cooling of the coil and mandril in the oven. The formation of surface oxidation is a concern, since it is considered a contaminant when introduced into the bloodstream of a patient. After the coil and mandril are stress relieved, conically helically shaped coil 15 is removed from the mandril. Although the coil has been stress relieved and, in particular, heat treated, minimally spaced turns 24 of the coil on the mandril expand to a spacing that increases proximally from the distal end of the coil.

FIG. 6 depicts conically helically shaped coil 15 of FIG. 5 after it has been removed from the mandril. The conically

helically shaped coil has a plurality of radially expanding turns 16 with spacing 21 that increases proximally from distal turn 17 to proximal turn 19. As previously indicated, distal turn 17 has minor diameter 18, whereas proximal turn 19 has major diameter 20. Spacing 21 between radially expanding turns 16 is typically no more than 2 mm in width at distal turn 17 and increases proximally to a maximum spacing of 5 mm at proximal turn 19.

FIG. 7 depicts an end view of conically helically shaped coil 15 of FIG. 6. Radially expanding turns 16 of the coil are readily observed from this end view. Thus, it can be more readily appreciated how the radially expanding turns of the embolization coil nearly cover the entire cross-sectional area of a vessel lumen. Thrombogenic fibers of, for example, commercially available .00075" diameter Z-twist, DACRON fiber material are placed at periodic intervals along the length of the coil in minimal spacing 27 between tightly spaced turns 13 of the longitudinally extending coil.

FIG. 8 depicts a partially sectioned view of shipping cannula 28 with embolization coil 10 inserted therein in a stretched condition. By way of example, the shipping cannula is a 21 gauge thin wall stainless steel tube with Luer-lock fitting 43 at the proximal end thereof. The embolization coil is positioned in this cannula for introduction into a guiding or delivery catheter for introduction at the occlusion site. Normally, the guiding or delivery catheter is percutaneously positioned at the occlusion site. The embolization coil is then transferred from the shipping cannula into the delivery catheter with an introducer stylet that is inserted through the proximal end of the shipping cannula and into the passage of the delivery catheter. To ensure proper placement of the embolization coil, distal end 29 of the embolization coil is positioned proximate distal end 30 of the shipping cannula with proximal end 31 positioned proximate the proximal end of the cannula.

It is to be understood that the above-described embolization coil is merely an illustrative embodiment of the principles of this invention and that other heat treated or stress relieved embolization coils may be devised by those

skilled in the art without departing from the spirit and scope of this invention. Furthermore, other conically helically shaped coils with spacing that increases proximally between the radially expanding turns of the coil may also be devised by those skilled
5 in the art without departing from the spirit and scope of the invention. Although the embolization coil has been stress relieved by way of a heat treatment process, other stress relieving treatment processes are contemplated, such as through mechanical, chemical, or electrical processes.

10

HELICAL EMBOLIZATION COIL

Claims

- 5 1. An embolization coil (10) comprising:
a continuous wire strand (11) wound into a longitudinally
extending coil (12) having a plurality of spaced turns (16), said
longitudinally extending coil being in a conically helically
shaped formation (15) in which the turns are radially expanding,
10 a distal turn (17) of said radially expanding turns having a
minor diameter (18) which is less than a minimum diameter (34) of
a vessel (32) in which said embolization coil is to be positioned
therein, and a proximal turn (19) of said radially expanding
turns having a major diameter (20) greater than a maximum
15 diameter (33) of a vessel of which said embolization coil is to
be positioned therein.
2. The embolization coil of claim 1 wherein said radially
expanding turns include spacing (21) therebetween that increases
20 proximally.
3. The embolization coil of claim 1 wherein said conically
helically shaped coil is heat treated to relieve stresses that
are formed when winding said longitudinally extending coil and
25 said conically helically shaped coil.
4. The embolization coil of claim 1 wherein said continuous wire
strand comprises a metallic material (22) and wherein said
conically helically shaped coil is formed by winding said
30 longitudinally extending coil around a longitudinally tapered
mandril (23) with a plurality of minimally spaced turns (24),
heating said conically helically shaped coil when wound around
said longitudinally tapered mandril at a stress relief
temperature of said metallic material for a first time period,
35 and cooling said conically helically shaped coil when wound
around said longitudinally tapered mandril from said stress

relief temperature for a second time period greater than said first time period.

5. The embolization coil of claim 4 wherein said continuous wire strand comprises a metallic alloy (22) that is substantially free of surface oxidation and wherein said longitudinally tapered mandril comprises a material (25) that remains substantially free of surface oxidation during heating and cooling of said conically helically shaped coil.

10

6. The embolization coil of claim 5 wherein said metallic alloy comprises at least one from a group consisting of platinum, stainless steel, iridium, palladium, tungsten, and gold.

7. The embolization coil of claim 1 wherein said conically helically shaped coil is heated at a stress relief temperature of said continuous wire strand for a first time period and then gradually cooled down from said stress relief temperature for a second time period greater than said first time period.

20

8. The embolization coil of claim 1 wherein said continuous wire strand comprises a metallic material (22) that is substantially free of surface oxidation.

9. The embolization coil of claim 1 further comprising thrombogenic fibers (26) positioned in said plurality of tightly spaced turns of said longitudinally extending coil.

10. An embolization coil (10) comprising:

a continuous wire strand (11) wound into a longitudinally extending coil (12) having a plurality of spaced turns (16), said longitudinally extending coil being in a conically helically shaped formation (15), said continuous wire strand being stress relieved after said longitudinally extending coil is wound into said conically helically shaped coil.

11. The embolization coil of claim 11 wherein said conically helically shaped coil has a plurality of radially expanding turns (16), a distal turn (17) thereof having a minor diameter (18) less than a minimum diameter (34) of a vessel (32) of which said embolization coil is to be positioned therein and a proximal turn (19) thereof having a major diameter (20) greater than a maximum diameter (33) of the vessel of which said embolization coil is to be positioned therein.

12. The embolization coil of claim 10 wherein said conically helically shaped coil is stress relieved.

13. The embolization coil of claim 10 wherein said conically helically shaped coil has a plurality of radially expanding turns (16) and wherein said radially expanding turns have a spacing (21) therebetween that increases from a distal turn (17) to a proximal turn (19) thereof.

14. The embolization coil of claim 10 wherein said conically helically shaped coil is formed by winding said longitudinally extending coil around a longitudinally tapered mandril (23) with a plurality of minimally spaced turns (24) and wherein said conically helically shaped coil when wound around said longitudinally tapered mandril is heat treated to relieve residual stresses formed therein.

15. The embolization coil of claim 10 wherein said continuous wire strand comprises a metallic alloy (22) including at least one from a group consisting of platinum, stainless steel, iridium, palladium, tungsten, and gold.

16. The embolization coil of claim 15 wherein said conically helically shaped coil is formed by winding said longitudinally extending coil around a longitudinally tapered mandril (23) and wherein said conically helically shaped coil is heated at a stress relief temperature of said metallic alloy for a first time

period and then cooled down from said stress relief temperature for a second time period greater than said first time period.

17. The embolization coil of claim 10 further comprising
5 thrombogenic fibers (26) positioned in said tightly spaced turns at predetermined intervals therealong.




18. The embolization coil of claim 10 further comprising a
cannula (28) in which said conically helically shaped coil is
10 positioned therein.



19. The embolization coil of claim 18 wherein a distal end (29)
of said conically helically shaped coil is positioned proximate
a distal end (30) of said cannula and wherein a proximal end (31)
15 of said conically helically shaped coil is positioned proximally
from said distal end thereof in said cannula.




20. An embolization coil (10) comprising:
a continuous wire strand (11) of a platinum-tungsten
20 alloy (22) wound into a longitudinally extending coil (12) having
a plurality of tightly spaced turns (13), said longitudinally
extending coil wound into a conically helically shaped coil (13)
having a plurality of radially expanding turns (16), said
conically helically shaped coil being formed by winding said
25 longitudinally extending coil around a longitudinally tapered
mandril (23) with a plurality of minimally spaced turns (24),
heating said conically helically shaped coil for a first time
period at a stress relief temperature of said platinum-tungsten
alloy to relieve stresses formed therein, and then cooling said
30 conically helically shaped coil down from said stress relief
temperature over a second time period greater than said first
time period to minimize formation of new residual stresses
therein, a distal end of said radially expanding turns having a
minor diameter (18) less than a minimum diameter (34) of a vessel
35 (32) of which said embolization coil is to be positioned therein,
a proximal turn (19) of said radially expanding turns having a
major diameter (20) greater than a maximum diameter (33) of a

vessel of which said embolization coil is to be positioned therein, said radially expanding turns including proximally increasing spacing (21) from said distal turn to said proximal turn; and

- 5 thrombogenic fibers (26) positioned in said plurality of tightly spaced turns.







INTERNATIONAL SEARCH REPORT

Int. l. Application No
PCT/US 95/03380

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 A61F2/01 A61B17/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 A61F A61B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X,P	WO,A,94 07560 (TARGET THERAPEUTICS, INC.) 14 April 1994 see page 6, line 27-30; figure 1 AND 11 ---	1,2, 9-11,13, 17-20
X,P	WO,A,94 09705 (TARGET THERAPEUTICS, INC.) 11 May 1994 see page 7, line 1-5; figure 9 AND 16 ---	1,2, 9-11,13, 17-20
Y	US,A,5 226 911 (CHEE ET AL.) 13 July 1993 see column 2, line 4-11 - column 3, line 1-19; figures 1,2 --- -/--	1,2, 9-11,13, 17-20

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

11 July 1995

Date of mailing of the international search report

03.08.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Ehrsam, F

INTERNATIONAL SEARCH REPORT

Int. Application No.

PCT/US 95/03380

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US,A,4 994 069 (RITCHART ET AL.) 19 February 1991 see column 6, line 6-15; figures 5-7 ---	1,2, 9-11,13, 17-20
A	US,A,5 190 546 (JERVIS) 2 March 1993 see column 3, line 33-62; figures 1,2 ---	3,5-8, 12,15, 16,20
A	WO,A,92 16163 (ETHNOR) 1 October 1992 see figures 1-3,15,17 ---	1,10,20
A	US,A,5 192 301 (KAMIYA ET AL.) 9 March 1993 see column 7, line 8-21; figure 25 ---	1,10,20
A,P	WO,A,94 06503 (TARGET THERAPEUTICS, INC.) 31 March 1994 see page 16, line 1-31; figure 15 ---	
A	WO,A,93 06884 (TARGET THERAPEUTICS, INC.) 15 April 1993 see figure 1 AND 11 -----	1,10,20

INTERNATIONAL SEARCH REPORT

 Int. Application No
 PCT/US 95/03380

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
WO-A-9407560	14-04-94	US-A-	5304194	19-04-94
		AU-B-	656283	27-01-95
		AU-B-	5137193	26-04-94
		EP-A-	0615459	21-09-94
		JP-T-	6510938	08-12-94

WO-A-9409705	11-05-94	US-A-	5382259	17-01-95
		AU-B-	659970	01-06-95
		AU-B-	5540094	24-05-94
		CA-A-	2109283	27-04-94
		EP-A-	0618783	12-10-94
		JP-A-	6319743	22-11-94
		NO-A-	942025	01-06-94

US-A-5226911	13-07-93	AU-A-	2686292	03-05-93
		AU-A-	2868692	03-05-93
		CA-A, C	2084749	03-04-93
		CZ-A-	9400666	15-06-94
		EP-A-	0606392	20-07-94
		FI-A-	941499	16-05-94
		NO-A-	941061	23-03-94
		NZ-A-	244607	26-08-94
		PT-A-	100927	30-06-94
		WO-A-	9306883	15-04-93
		WO-A-	9306884	15-04-93
		US-A-	5304194	19-04-94

US-A-4994069	19-02-91	NONE		

US-A-5190546	02-03-93	US-A-	5067957	26-11-91
		US-A-	4665906	19-05-87
		CA-A-	1246956	20-12-88
		EP-A, B	0145166	19-06-85
		JP-A-	7067951	14-03-95
		JP-A-	60100956	04-06-85

WO-A-9216163	01-10-92	FR-A-	2673830	18-09-92
		FR-A-	2683714	21-05-93
		EP-A-	0575478	29-12-93
		JP-T-	6505660	30-06-94

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 95/03380

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9216163		US-A- 5413586	09-05-95
US-A-5192301	09-03-93	FR-A- 2641692	20-07-90
		JP-A- 2277459	14-11-90
WO-A-9406503	31-03-94	US-A- 5250071	05-10-93
		AU-B- 4857793	12-04-94
		CA-A- 2119772	31-03-94
		DE-U- 9320840	02-03-95
		EP-A- 0617632	05-10-94
		FI-A- 942276	16-05-94
		JP-T- 7502674	23-03-95
		NO-A- 941363	15-04-94
WO-A-9306884	15-04-93	US-A- 5226911	13-07-93
		AU-A- 2686292	03-05-93
		AU-A- 2868692	03-05-93
		CA-A, C 2084749	03-04-93
		CZ-A- 9400666	15-06-94
		EP-A- 0606392	20-07-94
		FI-A- 941499	16-05-94
		NO-A- 941061	23-03-94
		NZ-A- 244607	26-08-94
		PT-A- 100927	30-06-94
		WO-A- 9306883	15-04-93
		US-A- 5304194	19-04-94